

### Interior / Exterior Acrylic Polyurethane Finish Architectural Coating - Premium Plus

#### Description

Polytec DTM Semi-Gloss is a premium plus exterior, single component, high performance architectural and light industrial coating, which is uniquely formulated with a combination of high performance self-crosslinking acrylic and polyurethane polymers fused with proprietary resin technologies. This product was developed for use as a DTM over ferrous and non-ferrous metals. Additionally this product may be used over a wide variety of surfaces including wood, concrete, masonry, aged alkyds and various plastics. **Polytec DTM Semi-Gloss** can be used under extreme environmental conditions. It offers excellent flash rust, long term corrosion & abrasion resistance. This product also provides resistance to abrasions, stains, moisture and both household & industrial chemicals. It has excellent color & gloss retention, does not yellow, is fast dry and suitable for use in USDA inspected facilities.

#### Recommended Uses

Ideal for use on properly prepared and primed structural steel, equipment, metal doors, frames and wrought iron surfaces of all types. It can also be used over properly prepared concrete, masonry, wood, many commercially available plastics and ceramic surfaces. **NOT for use on surfaces exposed to hand oils, lanolin, on kitchen cabinets or table tops. For handrails, or surfaces exposed to hand oils, use the Polytec 5700 series product.**

#### Colors

White and Black  
Bases: A, D, H, & M

#### Packaging

One and five gallon containers

#### Finish

Semi-Gloss, sheen at 60° = 55.0% (+/- 3.0%)

#### Surface Preparation

Remove oil, grease, dirt, loose rust, loose peeling paint or other contaminants that may impair adhesion and affect performance. Glossy or slick surfaces should be lightly sanded. **Passivation coatings applied to galvanized metal must be removed prior to priming. Newly galvanized substrates should be tested for chromates. Refer to SSPC SP-16 for proper testing and surface preparation.**

#### Primer

Concrete/Masonry:	4000 Uniprime 8000 Carefree Prime-ZALL
Wood:	4000 Uniprime 8000 Carefree Prime-ZALL
Metal Non-Galvanized:	8600 Polytec Primer 9600 Protec Metal Prime
Metal Galvanized:	8600 Polytec Primer 4800 Metal Pro Primer
Aluminum:	8600 Polytec Primer

#### Application

Brush, roll or spray. Ambient and surface temperatures must be above 50°F and relative humidity below 80%. Clean tools and equipment with soap and water.

**DISCLAIMER:** To the best of our knowledge, the technical data contained herein are true and accurate at the date of issuance and offered in good faith. All technical information is subject to change without prior notice. This product is guaranteed to give satisfactory performance if applied and used in accordance with the label instructions. Any liability shall be limited to a refund of the purchase price, or replacement of this product. This warranty does not include labor or cost of labor for the application of any coating. All express and all implied warranties are hereby disclaimed and excluded including all implied warranties of fitness for a particular use and merchantability. Final determination of the suitability of product or intended use is the sole responsibility of the user. Additional information may be obtained from your local sales representative.

#### Drying Time

Touch: 1 hour  
Recoat: 3 hours

#### Coverage

Up to 350 square feet per gallon, depending on porosity and texture of the surface.

#### Thickness

Wet = 5.0 mil      Dry = 2.0 mil

#### Thinning

Use water sparingly.

#### Composition

Titanium Dioxide	23.0%
Extenders	2.4%
<b>TOTAL PIGMENT</b>	<b>25.4%</b>
Proprietary Resin	26.3%
Additives	4.5%
Water	43.8%
<b>TOTAL VEHICLE</b>	<b>74.6%</b>

Weights & Measurements +/-3.0%

Solids by Volume:	38.0%
Solids by Weight:	50.0%
VOC:	<50 g/l
Weight Per Gal:	10.14 lbs.
Viscosity:	100 - 110 KU

#### Testing

Adhesion (ASTM D 3359-97)	on steel panel	0% Removal
Prohesion (ASTM D 5894-96)	on steel panel (1000 hours)	No Corrosion
Humidity Resistance (ASTM D 4587-91)	on steel panel (100 hours)	10 (no effect)

#### Conformance

**SCAQMD** - complies with Rule 1113, Architectural Coatings.  
**LEED** - complies with LEEDv4  
**CDPH Section 01350** - Standard Method V1.2 2017



Products bearing this logo are Non-EG Certified. Ethylene Glycol (EG), is listed as a toxic air contaminant and hazardous pollutant. EG is a solvent used in some water-based paints. Vista Paint has replaced EG with non-toxic alternative solvents. Any Vista Paint product with this logo is formulated without EG (Non-EG).



Vista Paint is the industry leader when it comes to relying on renewable energy. At Vista Paint, our products are manufactured using 100% solar energy.

Last Updated 04.2024

